



Scan for product's Safety Data Sheet



Great Looking Floors.
Less Maintenance.

Pro-Link, Inc.
Canton, MA 02021
T: 800-745-4657
F: 781-828-9551
www.prolinkhq.com

Pro-Link® is a registered trademark of Pro-Link, Inc.

Copyright © 2017, Pro-Link, Inc. All rights reserved.



SPOT LIGHT™

HIGH GLOSS FINISH

- Extremely high gloss with superior film clarity.
- Unmatched response to high-speed burnishing.
- Clear formula creates a deep gloss providing a true “wet look.”
- Versatile - can be buffed or burnished.
- High solids.

DIRECTIONS

PREPARATION: If stripping is necessary, use a high quality stripper, and follow the directions accordingly. Follow with a thorough rinsing, and allow floor to dry completely. If stripping is not necessary, sweep up loose dirt and dust. Clean with a quality cleaner to remove dirt and oils. Follow with a thorough rinsing, and allow floor to dry completely.

FINISHING: Spread a liberal coat of finish evenly across the floor with a clean mop or applicator. Allow each coat to dry at least 30 minutes before applying the next coat. Four coats is ideal initially, depending on the condition of the floor and desired gloss.

MAINTENANCE: The floor may be maintained using a quality floor cleaner and damp mopping regularly. Spray buffing or mop-on restoring may also be done after sweeping up loose dirt and dust. Follow directions for each product accordingly.

This product meets the maximum content requirements for Volatile Organic Compounds (VOCs) as established by state and Federal regulations



FLOOR COATING AND FINISHING MATERIAL AS TO SLIP RESISTANCE ONLY 17SU



- Item # B14082**
1 Gallon/4 per Case
- Item # B14083**
2.5 Gallon/2 per Case
- Item # B14084**
5 Gallon
- 25% Solids**

TECHNICAL DATA

Color.....	Milky emulsion
Odor	Mild
pH	8.0 - 9.0
Coverage	1800 – 2200 ft ² / gal.
Dry/Recoat Time	30 minutes min.
Maintenance Schedule.....	Weekly spray buffing or burnishing
Detergent Resistance.....	Excellent
Leveling.....	Excellent
Removability	With instant type strippers
Slip Resistance	0.5 min. by ASTM-D2047
VOC Content	0.48 lbs./gal.
Storage/Stability	1 year
Weight per Gallon	8.66lbs./gal.
Freeze / Thaw Stability.....	Keep from freezing